

Product	Colour	Viscosity at 40 °C [mm ² /s]	Application
BZK II	Amber	ca. 50	Galvanised sheet metal; excellent protection against white rust; deep drawing and profile rolling; Mix ratio with water: 10 to 30 %
BZK ST	Amber	ca. 46	Steel; excellent corrosion protection; deep drawing and profile rolling; mix ratio with water: 5 to 30 %
ECLF 100 N	Amber	70	Steel, aluminium, rustproof sheet metal; large-scale deep drawing parts; stamping and bending operations; Mix ratio with water: 5 to 20 %
D ECLF	Yellow	100	Steel, non-ferrous metals, aluminium; ester-based synthetic special lubricant; also suitable for chipping; Mix ratio with water: 5 to 10 %
BZK XI	Amber	ca.100	Steel; rostproof steel; semisynthetically, waterbased, stamping and drawing oils, without chlorinated additives

The above mentioned information on the area of application are based on lab tests and practical experiences. These instructions do not release the user from checking the suitability of the lubricant and its application and follow-up processes.
We reserve the rights to make changes due to new laws, regulations, perceptions, etc.